

# SYDNEY

Finish	Blockout
Application	Roller   Roman   Panel
Composition	100% Polyester
Width	290cm   114 inches
Roll Size	20m   22yd
Weight	415 gsm
Thickness	0.7mm   0.02 inches
Colourfastness AS 2001.2.21:1989	7
Opacity to Light AS2663.3:1999 Appendix B	100%
Care Instructions	Do not allow dust to accumulate. Regularly gently vacuum with appropriate attachment. Do not wash. Do not dry clean. Warm iron if needed. Test in inconspicuous area with mild detergent solution prior to spot cleaning. Do not allow blind to become fully wet, use damp cloth only.



[WWW.WILSONFABRICS.COM.AU](http://WWW.WILSONFABRICS.COM.AU)

[WWW.WILSONFABRICS.COM](http://WWW.WILSONFABRICS.COM)

# WHY WILSON FABRICS?



Australian Made  
Made to protect you and your interior for many years to come.



PITCH BLACK™ Blockout Coating  
Wilson Fabrics Blockout Coated fabrics are full blockout that surpass blockout standards.



StainProtect™  
Protected by StainProtect™ which repel stains and spills.



Fade Resistant  
Stringently tested for colourfastness to light ensuring they will stand the test of time.

**Ultraviolet**  
Protection Factor



Excellent Protection  
ARPANSA UPF RATING

UPF50+ Sun Protection  
Highest UPF rating, providing "Excellent Protection" from the harmful ultraviolet radiation. Our fabrics let through 0.000 of UVA and 0.000 UVB rays ensuring quality protection from the sun, protecting you and your home.



PVC & Lead Free  
Fabrics containing PVC and Lead can not only emit carcinogens in the home, the manufacturing process is also 'dirty' as toxic and carcinogenic components are required for manufacture. Hence why we only develop PVC and Lead Free Fabrics, better for you and the environment.



Fire Retardancy  
Australian Standards only.  
AS1530.3 Results available upon request.



5 Year Limited Warranty  
Giving you peace of mind and long lasting quality.

DO YOU NEED MORE REASONS?



# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106  
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400

## TEST REPORT

**Client :** Australian Textile Mills Pty Ltd  
Sisely Avenue  
Wangaratta VIC 3677

**Test Number :** 20-002089  
**Issue Date :** 6/05/2020  
**Print Date :** 6/05/2020

**Sample Description** Clients Ref : "Sydney Style: 7124 S/O: 2218807"  
Woven backcoated fabric  
Colour : Charcoal  
End Use : Roman blackout blind  
Nominal Composition : 100% Polyester  
Nominal Mass per Unit Area/Density : 417.3g/m2  
Nominal Thickness : 0.66mm

AS/NZS 1530.3-1999

### Methods for Fire Tests on Building Materials, Components and Structures Part 3: Simultaneous Determination of Ignitability, Flame Propagation, Heat Release and Smoke Release

Face tested:	Face		
Date tested:	06/05/2020		
	Standard Error		Mean
Ignition time	0.35		7.19 min
Flame propagation time	1.2		13.2 sec
Heat release integral	3.2		117.0 kJ/m <sup>2</sup>
Smoke release, log d	0.0061		-0.5338
Optical density, d			0.2927 / metre
Number of specimens ignited:			6
Number of specimens tested:			6
Regulatory Indices:			
Ignitability Index			13 Range 0-20
Spread of Flame Index			9 Range 0-10
Heat Evolved Index			4 Range 0-10
Smoke Developed Index			6 Range 0-10

202543

43854

Page 1 of 2

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing  
- Chemical Testing : Accreditation No. 983  
- Mechanical Testing : Accreditation No. 985  
- Performance & Approvals Testing : Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc. (Hons)  
MANAGING DIRECTOR